

# WONPOONG

DATA NO : 4104-115  
 Products : Signflex II backlit 680gsm  
 Production date : 20th APR, 2010

Property		RESULT	TEST METHOD
Total weight(g/m <sup>2</sup> )		680	EN ISO 2286-2
Composition(g/m <sup>2</sup> )	Fabric	107	
	Covering	573	
Thickness(m/m)		0.6	
Cut strip tensile (N / 5cm)	Warp	1315	DIN 53354
	Weft	1620	
Elongation (%)	Warp	37	
	Weft	36	
Tongue tear (N)	Warp	245	DIN 53363
	Weft	310	
Endurance temperature	Min	-30	DIN 53361
	Max	+70	
ADHENSION (N / 5cm)	WARP	160	DIN 53357
	WEFT	142	
Standard roll(m)		50	
Base cloth			
Material		PES	DIN ISO 2076
Denier, Density		5000X1,000D(18X12/inch)	DIN ISO 2060

The above mentioned data should not be used for the purpose of a law-suit.  
 Wonpoong Corporation, R&D department.

WONPOONG CORPORATION

VL/LB  
 Date

*San Wook*  
 4.20.2010